

# SISER HTV Time/Temp Chart

HTV Style	Temp.*	Time	Pressure	Peel	Layerable	Dryer Setting
Siser Easyweed	305°F / 150°C	10-15 sec.	medium	hot or cold	yes	normal
Easyweed Extra	305°F / 150°C	10-15 sec.	medium	hot or cold	yes	normal
Easyweed Electric	305°F / 150°C	10-15 sec.	medium	hot or cold	yes	normal
Easyweed Glow	305°F / 150°C	10-15 sec.	medium	hot or cold	yes	normal
Easyweed Stretch	320°F / 160°C	20 sec.	firm	hot or cold	yes	normal
Easyweed Sub Block	265°F / 130°C	10-15 sec.	medium	hot or cold	yes	hang to dry
EasyPatterns	305°F / 150°C	10-15 sec.	medium	hot or cold	yes	normal
Glitter	320°F / 160°C	15-20 sec	medium	warm**	<b>no</b>	normal
Holographic	320°F / 160°C	15-20 sec	medium	cold	<b>no</b>	normal
StripFlock Pro	311°F / 155°C	10-15 sec.	medium	warm**	yes	normal
Sparkle	305°F / 150°C	10-15 sec.	medium	hot or cold	yes	normal
Easyweed Adhesive	275°F / 135°C	5-10 sec.	medium	hot	yes	normal
Blackboard	275°F / 135°C	15 sec.	medium	warm**	yes	normal
Metal	305°F / 150°C	10-15 sec.	medium	cold	yes	low
Brick 600	311°F / 155°C	20 sec.	medium/firm	cold	yes	low
Twinkle	305°F / 150°C	15 sec.	medium/firm	hot or cold	<b>no</b>	low
EasyReflective	305°F / 150°C	15 sec.	medium	warm**	yes	normal

 Suitable for cotton, polyesters, blends

 Suitable for cotton, polyesters, blends, lycra/spandex

***Snip to it!***

\* All Siser HTV products can be used with a home iron. Set temperature between “Cotton” and “Linen”

\*\* Wait 15 seconds before peeling cover sheet

source: <https://www.siserna.com/files/heat-transfer-vinyl-instructions.pdf>